


粒度分布測定結果

光学台	サンプルID1	
レコードNo.	サンプルID2	
測定日付	タイトル	合成雲母
測定時刻	シリアルNo.	
ファイル名		



要約データ	値
MV(um)	13.69
MN(um)	3.869
MA(um)	8.732
CS	0.68710
SD(um)	8.616


ピーク(um)	頻度(%)	幅(um)
16.23	68.30	15.44
5.387	31.70	3.598

Ch.	粒径(um)	頻度(%)	累積(%)	Ch.	粒径(um)	頻度(%)	累積(%)	Ch.	粒径(um)	頻度(%)	累積(%)	Ch.	粒径(um)	頻度(%)	累積(%)
1	704.0	0.00	100.00	26	80.70	0.00	100.00	51	9.250	4.13	40.04	76	1.060	0.00	0.00
2	645.6	0.00	100.00	27	74.00	0.00	100.00	52	8.482	4.21	35.91	77	0.972	0.00	0.00
3	592.0	0.00	100.00	28	67.86	0.00	100.00	53	7.778	4.19	31.70	78	0.892	0.00	0.00
4	542.9	0.00	100.00	29	62.23	0.00	100.00	54	7.133	4.01	27.51	79	0.818	0.00	0.00
5	497.8	0.00	100.00	30	57.06	0.00	100.00	55	6.541	3.67	23.50	80	0.750	0.00	0.00
6	456.5	0.00	100.00	31	52.33	0.12	100.00	56	5.998	3.27	19.83	81	0.688	0.00	0.00
7	418.6	0.00	100.00	32	47.98	0.25	99.88	57	5.500	2.83	16.56	82	0.630	0.00	0.00
8	383.9	0.00	100.00	33	44.00	0.42	99.63	58	5.044	2.43	13.73	83	0.578	0.00	0.00
9	352.0	0.00	100.00	34	40.35	0.69	99.21	59	4.625	2.09	11.30	84	0.530	0.00	0.00
10	322.8	0.00	100.00	35	37.00	1.10	98.52	60	4.241	1.81	9.21	85	0.486	0.00	0.00
11	296.0	0.00	100.00	36	33.93	1.62	97.42	61	3.889	1.57	7.40	86	0.446	0.00	0.00
12	271.4	0.00	100.00	37	31.11	2.27	95.80	62	3.566	1.35	5.83	87	0.409	0.00	0.00
13	248.9	0.00	100.00	38	28.53	2.97	93.53	63	3.270	1.15	4.48	88	0.375	0.00	0.00
14	228.2	0.00	100.00	39	26.16	3.73	90.56	64	2.999	0.95	3.33	89	0.344	0.00	0.00
15	209.3	0.00	100.00	40	23.99	4.31	86.83	65	2.750	0.75	2.38	90	0.315	0.00	0.00
16	191.9	0.00	100.00	41	22.00	4.71	82.52	66	2.522	0.57	1.63	91	0.289	0.00	0.00
17	176.0	0.00	100.00	42	20.17	4.84	77.81	67	2.312	0.41	1.06	92	0.265	0.00	0.00
18	161.4	0.00	100.00	43	18.50	4.75	72.97	68	2.121	0.30	0.65	93	0.243	0.00	0.00
19	148.0	0.00	100.00	44	16.96	4.55	68.22	69	1.945	0.22	0.35	94	0.223	0.00	0.00
20	135.7	0.00	100.00	45	15.56	4.23	63.67	70	1.783	0.13	0.13	95	0.204	0.00	0.00
21	124.5	0.00	100.00	46	14.27	3.99	59.44	71	1.635	0.00	0.00	96	0.187	0.00	0.00
22	114.1	0.00	100.00	47	13.08	3.83	55.45	72	1.499	0.00	0.00	97	0.172	0.00	0.00
23	104.7	0.00	100.00	48	12.00	3.78	51.62	73	1.375	0.00	0.00	98	0.158	0.00	0.00
24	95.96	0.00	100.00	49	11.00	3.84	47.84	74	1.261	0.00	0.00	99	0.145	0.00	0.00
25	88.00	0.00	100.00	50	10.09	3.96	44.00	75	1.156	0.00	0.00	100	0.133	0.00	0.00

累積(%)	粒径(um)
10.00	4.390
20.00	6.023
30.00	7.512
40.00	9.244
50.00	11.56
60.00	14.44
70.00	17.54
80.00	20.99
90.00	25.81
99.00	39.13

粒度分布測定結果

光学台	サンプルID1
レコードNo.	サンプルID2
測定日付	タイトル 硝子粉325メッシュ95%
測定時刻	シリアルNo.
ファイル名	



要約データ	値
MV(um)	16.20
MN(um)	2.094
MA(um)	8.139
CS	0.73718
SD(um)	10.78

ピーク(um)	頻度(%)	幅(um)
14.43	100.00	21.56

Ch.	粒径(um)	頻度(%)	累積(%)	Ch.	粒径(um)	頻度(%)	累積(%)	Ch.	粒径(um)	頻度(%)	累積(%)	Ch.	粒径(um)	頻度(%)	累積(%)
1	704.0	0.00	100.00	26	80.70	0.00	100.00	51	9.250	2.87	34.01	76	1.060	0.16	0.16
2	645.6	0.00	100.00	27	74.00	0.17	100.00	52	8.482	2.86	31.14	77	0.972	0.00	0.00
3	592.0	0.00	100.00	28	67.86	0.27	99.83	53	7.778	2.81	28.28	78	0.892	0.00	0.00
4	542.9	0.00	100.00	29	62.23	0.33	99.56	54	7.133	2.68	25.47	79	0.818	0.00	0.00
5	497.8	0.00	100.00	30	57.06	0.43	99.23	55	6.541	2.48	22.79	80	0.750	0.00	0.00
6	456.5	0.00	100.00	31	52.33	0.59	98.80	56	5.998	2.25	20.31	81	0.688	0.00	0.00
7	418.6	0.00	100.00	32	47.98	0.80	98.21	57	5.500	1.99	18.06	82	0.630	0.00	0.00
8	383.9	0.00	100.00	33	44.00	1.08	97.41	58	5.044	1.77	16.07	83	0.578	0.00	0.00
9	352.0	0.00	100.00	34	40.35	1.45	96.33	59	4.625	1.59	14.30	84	0.530	0.00	0.00
10	322.8	0.00	100.00	35	37.00	1.94	94.88	60	4.241	1.44	12.71	85	0.486	0.00	0.00
11	296.0	0.00	100.00	36	33.93	2.53	92.94	61	3.889	1.34	11.27	86	0.446	0.00	0.00
12	271.4	0.00	100.00	37	31.11	3.23	90.41	62	3.566	1.25	9.93	87	0.409	0.00	0.00
13	248.9	0.00	100.00	38	28.53	3.93	87.18	63	3.270	1.18	8.68	88	0.375	0.00	0.00
14	228.2	0.00	100.00	39	26.16	4.64	83.25	64	2.999	1.10	7.50	89	0.344	0.00	0.00
15	209.3	0.00	100.00	40	23.99	5.12	78.61	65	2.750	1.01	6.40	90	0.315	0.00	0.00
16	191.9	0.00	100.00	41	22.00	5.33	73.49	66	2.522	0.91	5.39	91	0.289	0.00	0.00
17	176.0	0.00	100.00	42	20.17	5.27	68.16	67	2.312	0.81	4.48	92	0.265	0.00	0.00
18	161.4	0.00	100.00	43	18.50	4.93	62.89	68	2.121	0.71	3.67	93	0.243	0.00	0.00
19	148.0	0.00	100.00	44	16.96	4.49	57.96	69	1.945	0.61	2.96	94	0.223	0.00	0.00
20	135.7	0.00	100.00	45	15.56	3.96	53.47	70	1.783	0.52	2.35	95	0.204	0.00	0.00
21	124.5	0.00	100.00	46	14.27	3.53	49.51	71	1.635	0.45	1.83	96	0.187	0.00	0.00
22	114.1	0.00	100.00	47	13.08	3.21	45.98	72	1.499	0.38	1.38	97	0.172	0.00	0.00
23	104.7	0.00	100.00	48	12.00	3.00	42.77	73	1.375	0.32	1.00	98	0.158	0.00	0.00
24	95.96	0.00	100.00	49	11.00	2.90	39.77	74	1.261	0.28	0.68	99	0.145	0.00	0.00
25	88.00	0.00	100.00	50	10.09	2.86	36.87	75	1.156	0.24	0.40	100	0.133	0.00	0.00

累積(%)	粒径(um)
10.00	3.582
20.00	5.929
30.00	8.198
40.00	11.08
50.00	14.43
60.00	17.60
70.00	20.79
80.00	24.61
90.00	30.75
99.00	54.25